



AMANI ACRYLIC PLASTER PRIMER

PRODUCT DATA INFORMATION SHEET

PRODUCT DESCRIPTION:

A SMOOTH, WATER BASED ALKALI RESISTANT PRIMER.

FEATURES & BENEFITS:

- Suitable for interior or exterior use on either new or previously painted walls that have been properly prepared.
- A smooth primer for paints.
- Superior, alkali resistant.
- Controlled water vapour permeability enabling the substrate to “breathe”.
- Deep penetration for excellent adhesion
- Rapid drying properties
- Colour tinted close to the finishing coat
- Supplied ready to use.
- Eco friendly and water based. LOW VOC LEVEL [20g/L]

USES:

Designed for interior or exterior use as a primer for the Amani Paint range. The walls need to be suitably prepared to remove imperfections.

PACKAGING:

5L and 20L containers.

Spread rate: 6 to 8 m² per litre per coat

REFURB BUILD TIPS:

- Prepare the surface by removing all loose and flaking paint, dirt, grease, and grime.
- Make sure plasterwork is sound, dry, and clean.
- Don't skimp on the preparation work, repair cracks, blow holes etc.
- Has the waterproofing been done by a professional?
- Ensure that any scaffolding is positioned at a comfortable distance away from the wall so that the application technique is not compromised. (400-600mm).

Phone
+27 21 797 4250

Amani Coatings (Pty) Ltd
Reg. No. Rep. South Africa
1998/020176/07

info@amanicoatings.com
www.amanicoatings.com



AMANI ACRYLIC PLASTER PRIMER

NEW BUILD TIPS:

- Prepare the wall to ensure that the surface is clean, dry and sound.
- Inspect the substrate: The plaster substrate must have a smooth and even finish. This can be achieved with a steel float. The new plaster should be allowed to cure. This may take up to 21 days, depending on weather conditions. Test that it is dry before application. The moisture reader should show a saturation level of less than 12%.

FOR REFURBISHMENT & NEW BUILD:

- Apply 1 even coat of **AMANI ACRYLIC PLASTER PRIMER** and allow to dry.
- If the surface is very dense or porous do not apply. The applicator needs to assess the primers and preparation required once he has reviewed the substrate.
- The spread rate is 6 to 8 square meters per litre per coat.
- The spread rate is a guideline only. The applicator needs to determine the actual spread rate.
- The product is supplied ready for use. **DO NOT THIN.**
- Clean with water.

APPLICATION METHOD

- Apply **AMANI ACRYLIC PLASTER PRIMER** by brush or roller.
- **Do not apply on extremely porous substrates.**
- Apply at a spread rate of 6 – 8 m² /L / coat
- Number of coats: 1 or 2 coats to new surfaces to achieve complete obliteration. Allow to dry between coats.
- **Wet Film Thickness:** 125 - 167 µ per coat **Dry Film Thickness:** 40 - 53 µ per coat

SHELFLIFE AND STORAGE:

- 6 - 8 Months in unopened containers.
- Store in a cool, dry and well-ventilated place away from excessive heat or open flame.
- Do not allow to freeze.

CLIMATE CONDITIONS:

- **Amani Acrylic Plaster Primer** cannot be exposed to heavy rainfall before the coating has cured for 24 hours,
- The coating should never be applied in adverse weather conditions or on wet surfaces.
- In hot temperatures try not to apply in direct sunlight if possible.
- Variations in temperature will affect drying times.



AMANI ACRYLIC PLASTER PRIMER

HANDLING AND SAFETY:

This product is water based and non-toxic. Keep out of reach of children. It does contain chemicals that may be irritants to the skin. Appropriate protective clothing must be worn. Protect eyes and skin from exposure. Wash spillages immediately with water. Do not induce vomiting if swallowed. Consult a physician if irritation of skin persists or if product is ingested. Gather up environmental spillages and dispose of in accordance with regulations of the local authorities.

DISCLAIMER:

All information given here is given in good faith. We reserve the right to make changes to the product in the interests of product development and improving technology. Any queries please e-mail info@amanicoatings.com

Phone
+27 21 797 4250

Amani Coatings (Pty) Ltd
Reg. No. Rep. South Africa
1998/020176/07

info@amanicoatings.com
www.amanicoatings.com
